

# Chemlok® 8116 Adhesive

## Technical Data Sheet

Chemlok® 8116 adhesive is a one-coat, water-based adhesive used for vulcanization/bonding of peroxide-cured elastomers to zinc phosphatized steel and other rigid substrates.

With good resistance to hot oils, hot water and other engine fluids, Chemlok 8116 adhesive is suitable for use in the manufacture of gaskets, seals and NVH components.

### Features and Benefits:

**Convenient** – requires only a single coat for most applications, reducing labor, inventory and shipping costs.

**Environmentally Preferred** – uses water for dilution; provides reduced VOC emissions.

**Versatile** – bonds a wide range of silicone compounds to many rigid substrates, such as zinc phosphatized steel, nylon and aluminum.

**Environmentally Resistant** – provides good resistance to high temperature fluid environments; excellent for use in gasket or seals.

### Elastomers:

- Nitrile (NBR) - peroxide cure
- Hydrogenated Nitrile (HNBR) - peroxide cure
- Carboxylated HNBR (XHNBR)
- Fluoroelastomer (FKM) - peroxide cure/AFLAS
- Silicone (VMQ, PMQ, PVMQ, FVMQ) - peroxide cure
- EPDM Polymers
- Vamac - peroxide cure
- Peroxide-cured Elastomers

### Application:

**Surface Preparation** – Thoroughly clean metal surfaces prior to application. Remove protective oils, cutting oils and greases by solvent degreasing or alkaline cleaning. Remove rust, scale or oxide coatings by suitable chemical or mechanical cleaning methods.

For further detailed information on surface preparation of specific substrates, refer to Chemlok Adhesives application guide.

### Typical Properties\*

Appearance	Black Liquid
Viscosity, cps @ 25°C (77°F) Brookfield LVT Spindle 2, 30 rpm	100 - 900
Density kg/m <sup>3</sup> (lb/gal)	1138 - 1174 (9.5 - 9.8)
Solids Content by Weight, %	32 - 36
Flash Point (Seta), °C (°F)	>93 (>200)
Solvents	Deionized Water

\*Data is typical and not to be used for specification purposes.



ENGINEERING YOUR SUCCESS.

**Mixing** – Stir adhesive for 10-20 minutes or until uniform in color. Make sure to lift solids from bottom of container. Do not shake. If dilution is needed, use deionized water.

**Applying** – Apply adhesive by spray or dip methods. For best results, preheat metal parts to 60-65°C (140-150°F) prior to spray application.

Regardless of application method, the dry film thickness of Chemlok 8116 adhesive should be 7.6-17.8 micron (0.3-0.7 mil).

**Drying/Curing** – Allow coated parts to air-dry for 30-60 minutes at room temperature. Use of heat forced air is recommended to thoroughly dry coated parts.

Chemlok 8116 adhesive cures during the rubber vulcanization process.

**Cleanup** – Use soap and water to remove wet adhesive. Remove dried adhesive with solvents such as acetone, MEK or alcohols.

## Shelf Life/Storage:

Shelf life is nine months from date of shipment when stored by the recipient at 21-27°C (70-80°F) in original, unopened container. Do not freeze product.

## Cautionary Information:

Before using this or any Parker LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

*For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.*

Values stated in this document represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as Parker LORD has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, Parker LORD does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

WARNING – USER RESPONSIBILITY. FAILURE OR IMPROPER SELECTION OR IMPROPER USE OF THE PRODUCTS DESCRIBED HEREIN OR RELATED ITEMS CAN CAUSE DEATH, PERSONAL INJURY AND PROPERTY DAMAGE.

This document and other information from Parker-Hannifin Corporation, its subsidiaries and authorized distributors provide product or system options for further investigation by users having technical expertise.

The user, through its own analysis and testing, is solely responsible for making the final selection of the system and components and assuring that all performance, endurance, maintenance, safety and warning requirements of the application are met. The user must analyze all aspects of the application, follow applicable industry standards, and follow the information concerning the product in the current product catalog and in any other materials provided from Parker or its subsidiaries or authorized distributors.

To the extent that Parker or its subsidiaries or authorized distributors provide component or system options based upon data or specifications provided by the user, the user is responsible for determining that such data and specifications are suitable and sufficient for all applications and reasonably foreseeable uses of the components or systems.



Parker LORD  
Engineered Materials Group

111 LORD Drive  
Cary, NC 27511-7923  
USA

phone +1 877 ASK LORD (275 5673)

www.lord.com