

Circalok™ 6403 A SLW/B Urethane Encapsulant

Description

LORD Circalok™ 6403 A SLW/B urethane encapsulant is a general purpose, two-component urethane designed for applications requiring a fast cure, mechanical shock-resistant system. Circalok 6403 A SLW/B urethane encapsulant does not contain MOCA or TDI.

Features and Benefits

Low Viscosity – maintains low viscosity for complete and void-free encapsulation.

Environmentally Resistant – provides excellent protection and resistance to moisture; exhibits excellent hydrolytic stability.

Electrically Insulative – provides excellent electrical insulation properties.

Broad Temperature Range – can be used on parts and devices that experience operating temperatures from -50°C to +120°C.

Application

Surface Preparation – Surfaces should be clean and dry for optimum performance.

Mixing – Thoroughly mix each component prior to combining resin and hardener. Mix Circalok 6403 A SLW resin with Circalok 6403 B hardener at a 22:10 ratio, by weight. Automatic meter/mix/dispense equipment may be used for high volume production.

Unless a closed-chamber mechanical mixer is used, air may be introduced into the encapsulant system during mixing. Evacuate air from encapsulant prior to application.

Applying – Pour encapsulant directly from mixing container on to application, or apply using automatic meter/mix/dispense equipment.

Curing – Allow encapsulant to cure for 30-45 minutes at 25°C, or for 5-10 minutes at 100°C. Complete cure will be achieved in 2-3 days at 25°C.

This time-at-temperature profile refers to the time the material should be allowed to cure once it reaches the target temperature. Allowance should be made for oven ramp rates, parts with large thermal mass and other circumstances that may delay material reaching the target temperature.

Cleanup – Use dry rag wipe to clean up equipment and spills while encapsulant is still wet.

Typical Properties*

	6403 A SLW Resin	6403 B Hardener	Mixed
Appearance	Amber Liquid	Amber Liquid	Amber Liquid
Viscosity, cps @ 27°C	750	1200	900
Specific Gravity	0.96	1.19	1.04
Gel Time, min	–	–	10-15

*Data is typical and not to be used for specification purposes.

LORD TECHNICAL DATA

Typical Cured Properties*

Volume Resistivity, ohm-cm @ 25°C ASTM D 257	1 x 10 ¹⁴
Hardness Shore A	80
Tensile Strength, psi	1935
Dielectric Strength, V/mil	600
Dielectric Constant @ 25°C 1 kHz	3.6
Dissipation Factor @ 25°C 1 kHz	0.14

*Data is typical and not to be used for specification purposes.

Shelf Life/Storage

Shelf life of each component is six months from date of manufacture when stored at 25-40°C in original, unopened container.

If stored or shipped at cooler temperatures, Circalok 6403 B hardener may crystallize. If crystals appear, gently warm hardener at 50-60°C to melt crystals before mixing with resin.

Cautionary Information

Before using this or any LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

Circalok and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

LORD Corporation World Headquarters

111 Lord Drive
Cary, NC 27511-7923
USA

Customer Support Center (in United States & Canada)

+1 877 ASK LORD (275 5673)

www.lord.com

For a listing of our worldwide locations, visit LORD.com.

©2016 LORD Corporation OD DS3563 (Rev.1 7/16)

LORD
AskUsHow™