

Thermoset EP-20 Epoxy Resin

Description

LORD Thermoset EP-20 epoxy resin is a general purpose, unfilled epoxy resin formulated for use with several Thermoset hardeners to obtain a variety of handling and cured properties. Thermoset EP-20 epoxy resin can be used in many applications including adhesive, laminating and electrical/electronic insulation.

Features and Benefits

Handling and cured properties of the two-component epoxy system are dependent on the hardener used with Thermoset EP-20 epoxy resin.

Thermoset Hardener No. 18

- **Low Viscosity** – maintains low viscosity for complete and void-free encapsulation.
- **Heat Resistant** – provides excellent heat resistance for a room temperature cured system.

Thermoset Hardener No. 65

- **Low Viscosity** – maintains low viscosity for complete and void-free encapsulation.
- **Excellent Appearance** – cures to a high gloss surface, free of “blush” or “sweat-out”.

Thermoset Hardener No. 66

- **Flexible Bond Strength** – provides high bond strength for use as an adhesive to a variety of surfaces. Rigidity of bond may be varied depending on mix ratio. A 1:2 (resin to hardener, by weight) ratio will yield a relatively flexible bond; a 2:1 ratio will provide a rigid bond.
- **Convenient** – provides a working life of over one hour; cures at room temperature or with mild elevated temperature.

Thermoset Hardener No. 67

- **Elevated Temperature Cure** – requires an elevated temperature cure to obtain a rigid bond.
- **High Temperature Resistant** – provides good resistance for cured system that experiences continuous operating temperature up to 155°C.
- **Chemically Resistant** – cured system provides excellent resistance to chemicals.

Thermoset Hardener No. 70

- **Low Viscosity** – provides low viscosity and surface tension, enabling void-free casting without a vacuum step.
- **Environmentally Resistant** – cured system provides excellent thermal shock resistance and high impact strength.

Thermoset Hardener No. 71

- **Low Exotherm** – exhibits low exothermic heat rise during room temperature cure.
- **Environmentally Resistant** – cured system provides excellent mechanical and thermal shock resistance; retains flexibility even after severe heat aging.

Typical Properties*

Appearance	Black Liquid
Viscosity, cps @ 25°C	13,000
Specific Gravity	1.17

*Data is typical and not to be used for specification purposes.

LORD TECHNICAL DATA

Application

Mixing – Transfer amount of resin needed to a clean container and add proper amount of hardener by weight. Thoroughly mix resin and hardener together. Automatic meter/mix/dispense equipment may be used for high volume production.

Unless a closed-chamber mechanical mixer is used, air will be introduced when catalyzing the mixture. Electrical properties of the epoxy are best when air bubbles and voids are minimized. Therefore, in extremely high voltage or other critical applications, vacuuming may be appropriate.

Applying – Apply epoxy system using automatic meter/mix/dispense equipment.

Curing – Cure time will vary depending on hardener used. Refer to cure schedule indicated below. This time-at-temperature profile refers to the time the material should be allowed to cure once it reaches the target temperature. Allowance should be made for oven ramp rates, parts with large thermal mass and other circumstances that may delay material actually reaching the target temperature.

Cleanup - Disposable containers and utensils are recommended when working with epoxies. However, when disposable materials are impractical, uncured epoxy can be removed by cleaning equipment with solvent. Solvent-cleaned utensils should be thoroughly dried before reuse; any remaining solvent can contaminate the next mixture.

Typical Properties* of Resin Mixed with Hardener

	Thermoset Hardener No. 18	Thermoset Hardener No. 65	Thermoset Hardener No. 66	Thermoset Hardener No. 67	Thermoset Hardener No. 70	Thermoset Hardener No. 71
Mix Ratio, Resin to Hardener						
by Weight	100:14	100:40	100:50	100:24	100:30	100:100
by Volume	100:16	100:50	100:60	100:30	100:35	100:120
Working Life, min @ 25°C	20	50	60	60	30	60
Cure Time, hr						
@ 25°C	24	24	24	–	24	24
@ 100°C	–	–	–	2**	–	–

Typical Cured Properties*

	Thermoset Hardener No. 18	Thermoset Hardener No. 65	Thermoset Hardener No. 66	Thermoset Hardener No. 67	Thermoset Hardener No. 70	Thermoset Hardener No. 71
Volume Resistivity, ohm-cm @ 25°C	1 x 10 ¹⁶	1 x 10 ¹⁵	1 x 10 ¹⁶	1 x 10 ¹⁶	2 x 10 ¹⁵	1 x 10 ¹⁴
Hardness Shore D, ASTM D 2240	88	85	85	92	82	60
Tensile Strength, MPa @ 25°C	77	62	52	75	60	16
Elongation at Break, %	3.6	4.5	12	5.2	3.5	55
Moisture Absorption, % 24 hours @ 25°C	0.18	0.22	0.35	0.20	0.36	0.85
Dielectric Constant 1 MHz @ 25°C	3.8	3.5	3.7	4.4	3.4	4.2
Dissipation Factor 1 MHz @ 25°C	0.020	0.016	0.016	0.038	0.025	0.021

*Data is typical and not to be used for specification purposes.

** Optional post cure - 2 hrs @ 150°C.

LORD TECHNICAL DATA

Shelf Life/Storage

Shelf life is two years from date of manufacture when stored at 25°C in original, unopened container. The material container must be periodically rotated to prevent settling.

Cautionary Information

Before using this or any LORD product, refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

"Ask Us How" is a trademark of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

LORD Corporation
World Headquarters

111 Lord Drive
Cary, NC 27511-7923
USA

Customer Support Center (in United States & Canada)

+1 877 ASK LORD (275 5673)

www.lord.com

For a listing of our worldwide locations, visit LORD.com.