

# CoolTherm™ EP-6035 Epoxy Encapsulant

## Description

LORD CoolTherm™ EP-6035 epoxy encapsulant is a two-component system recommended for use as a thermally conductive, thin bondline adhesive for attaching semi-conductors to heat sinks, and as a low viscosity potting and casting product for applications where thermal conductivity and non-burning properties are required.

## Features and Benefits

**Low Viscosity** – maintains low viscosity for complete and void-free encapsulation.

**High Thermal Conductivity** – provides high thermal conductivity for applications where superior heat transfer is required.

**Electrically Insulative** – provides excellent high voltage insulation.

**Low Exotherm** – exhibits low exotherm heat rise during room temperature cure.

**Broad Temperature Range** – can be used on parts and devices that experience operating temperatures from -65°C to +155°C.

**UL Rated** – provides excellent flame retardancy; UL 94 V-0 certified.

## Application

**Mixing** – Thoroughly mix each component prior to combining resin and hardener. Mix CoolTherm EP-6035 BLK resin with CoolTherm EP-6035 hardener at a 1:1 ratio, by weight or volume.

Thoroughly mix epoxy system. Be careful not to whip excessive air into the material. If necessary, remove entrapped air by evacuating material prior to pouring.

**Applying** – Apply encapsulant using automatic meter/mix/dispense equipment.

**Curing** – Allow encapsulant to cure for 24 hours at 25°C, or for 2 hours at 65°C. This time-at-temperature profile refers to the time the material should be allowed to cure once it reaches the target temperature. Allowance should be made for oven ramp rates, parts with large thermal mass and other circumstances that may delay material reaching the target temperature.

## Typical Properties\*

	EP-6035 BLK Resin	EP-6035 Hardener	Mixed
Appearance	Black Liquid	Tan Liquid	Black Liquid
Viscosity, cps @ 25°C	9500	14,000	12,000
Specific Gravity	1.60	1.55	1.57
Working Life, hr @ 25°C	–	–	2

\*Data is typical and not to be used for specification purposes.

# LORD TECHNICAL DATA

## Typical Cured Properties\*

Volume Resistivity, ohm-cm @ 25°C ASTM D 257	1 x 10 <sup>16</sup>
Thermal Conductivity, W/mK	1.0
Coefficient of Linear Thermal Expansion, ppm/°C	35
Hardness Shore D	75
Tensile Strength, psi	5000
Elongation at Break, %	5.0
Dielectric Strength, V/mil	475
Dielectric Constant @ 100 Hz	4.1
Dissipation Factor @ 100 Hz	0.025

\*Data is typical and not to be used for specification purposes.

## Shelf Life/Storage

Shelf life of each component is one year from date of manufacture when stored at 25°C in original, unopened container.

## Cautionary Information

Before using this or any LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

*For industrial/commercial use only.* Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

CoolTherm and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

### LORD Corporation World Headquarters

111 Lord Drive  
Cary, NC 27511-7923  
USA

### Customer Support Center (in United States & Canada)

+1 877 ASK LORD (275 5673)

[www.lord.com](http://www.lord.com)

For a listing of our worldwide locations, visit [LORD.com](http://LORD.com).

©2017 LORD Corporation OD DS4000 (Rev.4 10/17)

**LORD**  
AskUsHow™