

# Circalok™ 6402 Urethane Encapsulant

## Description

Circalok™ 6402 encapsulant is a general purpose, two-component urethane system which cures to a flexible material ideal for use as a coating, laminating adhesive or encapsulating compound. It can also be used as an excellent adhesive for many non-polar substrates, including rubber, metal and vinyl. Circalok 6402 encapsulant is suitable for use in applications such as electrical cable encapsulation, general marine sealing and caulking, water-resistant roll coverings, waterproof fabric coatings and general purpose casting compounds.

## Features and Benefits

**Low Stress** – exhibits low shrinkage and stress on components as it cures.

**Broad Temperature Range** – can be used on parts and devices that experience operating temperatures from -70 to +100°C.

**Environmentally Resistant** – provides excellent hydrolytic stability; cures to an abrasion resistant coating.

## Application

**Mixing** – Thoroughly stir each component within its shipping container prior to mixing together. Transfer amount of Circalok 6402 A resin needed to a clean container. Add Circalok 6402 B hardener at a ratio of 20 parts resin to 10 parts hardener, by weight. Thoroughly mix components until uniform in consistency. Automatic meter/mix/dispense equipment may be used for high volume production.

**Applying** – Apply encapsulant manually or by using automatic meter/mix/dispense equipment.

**Curing** – Allow encapsulant to initially cure for 30 minutes at 100°C, or for 2 hours at 65°C, or for 7 hours at 25°C. Depending on temperature of initial cure, complete cure will be achieved after 1-7 days at 25°C.

## Shelf Life/Storage

Shelf life of each component is six months from date of manufacture when stored in a dry environment at 25°C in original, unopened container.

Circalok 6402 components may crystallize during storage. If crystals appear, gently warm material to 60°C and mix carefully before use.

## Typical Properties\*

	6402 A Resin	6402 B Hardener	Mixed
Appearance	Black or Amber Liquid	Amber Liquid	Black Liquid
Viscosity, cps @ 25°C	7500	75	4000
Specific Gravity	0.92	1.03	1.00
Gel Time, min @ 25°C	–	–	60
Working Life, min @ 25°C	–	–	30

\*Data is typical and not to be used for specification purposes.

# LORD TECHNICAL DATA

## Typical Cured Properties\*

Volume Resistivity, ohm-cm @ 25°C ASTM D 257	1 x 10 <sup>15</sup>
Glass Transition Temperature (Tg), °C	-70
Hardness Shore A, ASTM D 2240	60
Tensile Strength, MPa ASTM D 638	5.69
Elongation at Break, % ASTM D 638	300
Dielectric Strength, V/mil	590
Dielectric Constant @ 25°C 10 kHz, ASTM D 150	3.81
Dissipation Factor @ 25°C 10 kHz, ASTM D 150	0.018

\* Data is typical and not to be used for specification purposes.

## Cautionary Information

Before using this or any LORD product, refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

*For industrial/commercial use only.* Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

Ciralok and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

### LORD Corporation World Headquarters

111 Lord Drive  
Cary, NC 27511-7923  
USA

### Customer Support Center (in United States & Canada)

+1 877 ASK LORD (275 5673)

[www.lord.com](http://www.lord.com)

For a listing of our worldwide locations, visit [LORD.com](http://LORD.com).

©2012 LORD Corporation OD DS4111 (Rev.0 11/12)

**LORD**  
AskUsHow™